

Test Report

Report No.: WTH19H01003965C-8 Date: Feb. 15, 2019 Page 1 of 3

Applicant: BAREBONES SYSTEMS, LLC.

Address: 1215 East Wilmington Avenue - Ste. 140 Salt Lake City, UT 84106

Report on the submitted sample(s) said to be:

Sample Name: Enamel Bowl

Sample Description: 1.Copper metal binding gray enamel bowl

2. Copper metal binding

Sample Material: Enamel glaze, Stainless steel binding ring

Sample No.: WTH19H01003965C03

Sample Received Date: Feb. 11, 2019

Testing Period: Feb. 11, 2019 - Feb. 15, 2019

Test Method: Please refer to the following page(s).

Test Result: Please refer to the following page(s).

Test Requested:	Conclusion	
1.As specified by client, to determine the extractable Lead(Pb), Cadmium(Cd) with reference to	PASS	
the demand of US FDA guidance 7117.07(11/29/05) and 7117.06(11/29/05).		
2.As specified by client, to determine the Leachable Arsenic(As), Cadmium(Cd), Lead(Pb) and		
Mercury(Hg) content in the submitted sample with reference to the American Food and Drug	PASS	
Administration(FDA) General Recognized As Safe (GRAS) Specification.		

Signed for and on behalf of HCT

Daniel Li

Fax: 0755-89594380

Unit D,Penglitai Industrial Estate, Longping Xi Road, Longgang District, Shenzhen

E-mail: hongcai@hct-test.com Service Tel: 400-0066-989



Test Report

Report No.: WTH19H01003965C-8 Date: Feb. 15, 2019 Page 2 of 3

Test Result(s):

1. US FDA guidance and CPG 7117. 06&07- Leachable Cadmium(Cd), Lead(Pb) content

Test Method: Refer to AOAC 973.82(2005)

Test Condition: Acetic acid 4%, 24hours / 22°C

Ho	Results					JC.		
Tested Items	MDL	1					Limit	
2		A	В	C	D	E	F	
Extractable Lead	0.1	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	2.0
Extractable Cadmium	0.01	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	0.5

Note:

μg/mL=microgramme per milliliter

MDL=Method Detection Limit

N.D.=Not Detected(less than method detection limit

The limit from CPG 7117.06 & CPG 7117.07.

Soak volume is 700 ml.

CPG 7117.06

Category	Criteria	Limit(µg/mL)		
Category	OTHER IN	Extractable Cadmium		
Flatware	average of 6 units	0.5		
Small Hollowware	any one of 6 units	0.5		
Large Hollowware	any one of 6 units	0.25		

CPG 7117.07

Catagory	Cuitouio	Limit(μg/mL) Extractable Lead		
Category	Criteria			
Flatware	average of 6 units	3.0		
Small Hollowware other than cups and mugs	any one of 6 units	2.0		
Cups/mugs	any one of 6 units	0.5		
Large Hollowware other than pitchers	any one of 6 units	1.0		
Pitchers	any one of 6 units	0.5		



Unit: µg/mL



Test Report

Report No.: WTH19H01003965C-8 Date: Feb. 15, 2019 Page 3 of 3

2. US FDA GRAS- Leachable Arsenic(As), Cadmium(Cd), Lead(Pb) and Mercury(Hg) content

Unit: mg/L

Test Items	Test Method/	Test Method/		Limit	
	Equipment	MIDL	2	Limit	
Leachable Arsenic(As)		0.1	N.D.	Banned	
Leachable Cadmium(Cd)	4% Acid extraction,	0.1	N.D.	Banned	
Leachable Lead(Pb)	ICP-OES	0.1	N.D.	Banned	
Leachable Mercury(Hg)		0.1	N.D.	Banned	

Note:

mg/L=milligrams per litre

MDL=method detection limit

N.D.=not detected(less than method detection limit)



The photo of the sample

***End ***

This report will go into effect with HCT stamp. This report could not be revised. This report is only responsible for the test result of submitted samples. Without written authorization, any copy of this report for propaganda is invalid.

HONGCAI TESTING TECHNOLOGY CO.,LTD

Web:www.hct-test.com

Unit D,Penglitai Industrial Estate, Longping Xi Road, Longgang District, Shenzhen

Tel: 0755-84616666 E-mail: hongcai@hct-test.com Service Tel: 400-0066-989 Fax: 0755-89594380