

Applicant: BAREBONES SYSTEMS, LLC.

1215 EAST WILMINGTON AVENUE-STE.

140 SALT LAKE CITY

UT 84106

Number: HKGH02425366 S1

Date: Apr 17, 2019

This is to supersede Report No. HKGH02425366 dated Apr 17, 2019

due to information update.

Submitted sample said to be

Item Name : Cutting Board Reference No. : CKW-361

Exporter Name : BAREBONES SYSTEMS, LLC

Exporter Address : 1215 EAST WILMINGTON AVENUE-STE 140, SALT LAKE CITY, UT

84106

Factory Name : ZHEJIANG HUANGYAN YUANQIAO INDUSTRIAL ARTS FACTORY Factory Address : No.47 Yuandian Road, Yuanqiao, Huangyan, Taizhou, Zhejiang.

Importer : A And F Corporation

Importer Address : 6-27-56 Shinjuku, Shinjuku Square 8F Shinjuku-ku, Tokyo ZIP 160-

0022

Country of Origin : China Quantity : 2 pieces

For and on behalf of : Intertek Testing Services HK Ltd.







Number: HKGH02425366 S1

Conclusion:

The submitted sample was tested under the following requirements requested by the applicant, subject to the information stated in the remark and attached page(s) for details:

Requirement Result **Pass**

Specifications and Standards and Testing Methods of "Foodstuffs", "Implements", "Containers and Packaging", "Toys" and "Detergents", Section III - Apparatus and Containers and Packages, (Notification No. 370 of Ministry of Health, Labour and Welfare, (1) 1959), under the Japan Food Sanitation Law (Law No. 233, 1947)

- Coloring Matters

Specifications and Standards and Testing Methods of "Foodstuffs", "Implements", "Containers and Packaging", "Toys" and "Detergents", Section III - Apparatus and Containers and Packages, (Notification No. 370 of Ministry of Health, Labour and Welfare, 1959), under the Japan Food Sanitation Law (Law No. 233, 1947) (2)**Pass**

- Synthetic Resin in General





Number: HKGH02425366 S1

(1) **Chemical Properties on Coloring Matters**

Test method:

Specifications and Standards and Testing Methods of "Foodstuffs", "Implements", "Containers and Packaging", "Toys" and "Detergents", Section III - Apparatus and Containers and Packages, (Notification No. 370 of Ministry of Health, Labour and Welfare, 1959), under the Japan Food Sanitation Law (Law No. 233, 1947).

Tested Component:

(A) Copper plated stainless steel with black surface coating (handle of board).

Requirement: No running of coloring matters was observed in the leaching solution

Leaching solution	Leaching condition	Result
		(A)
n-Heptane	At 25°C for 1 hour	NR
20% Ethanol	At 60°C for 30 minutes	NR
Water	At 60°C for 30 minutes	NR
4% Acetic acid	At 60°C for 30 minutes	NR

Remark:

No Running of coloring matters was observed NR

Date sample received: Mar 18, 2019, Mar 26, 2019 Testing period: Mar 18, 2019 to Apr 02, 2019







Number: HKGH02425366 S1

(2) Chemical Properties For Synthetic Resin in General

Test method:

Specifications and Standards and Testing Methods of "Foodstuffs", "Implements", "Containers and Packaging", "Toys" and "Detergents", Section III - Apparatus and Containers and Packages, (Notification No. 370 of Ministry of Health, Labour and Welfare, 1959), under the Japan Food Sanitation Law (Law No. 233,1947).

Tested Component :

(A) Copper plated stainless steel with black surface coating (handle of board).

Intended use of product: Temperature ≤ 100°C

Material type	Synthetic resin in general			
Parameter	Result	Limit	Conclusion	
i didiffeter	(A)		Conclusion	
i) General requirement				
Elution test				
Consumption of potassium permanganate	< 4 μg/ml	10 μg/ml	Pass	
Heavy metal (as lead)	< 1 µg/ml	1 μg/ml	Pass	
Material test				
Total cadmium (Cd)	< 5 μg/g	100 μg/g	Pass	
Total lead (Pb)	< 5 μg/g	100 μg/g	Pass	

Remark: µg/ml = microgram per millilitre

μg/g = microgram per gram

Date sample received: Mar 18, 2019

Testing period: Mar 18, 2019 to Apr 03, 2019





Number: HKGH02425366 S1















Number: HKGH02425366 S1





End of report

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: http://www.intertek.com/terms/. Intertek's responsibility and liability are limited to the terms and conditions of the agreement.

This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

This report shall not be reproduced, except in full.







To: BAREBONES SYSTEMS, LLC. Ref: FC-2019-3871

Date: Apr 29, 2019

Re: Report Revision Notification

Intertek Testing Services Report Number HKGH02425366 Dated Apr 17, 2019.

Please be informed that all the content recorded in the above captioned report will be void. This captioned report is now superseded by a revised Intertek Testing Services report, HKGH02425366 S1.

Thank you for your attention.

For and on behalf of :

Intertek Testing Services HK Ltd.

Angel Y.F. Cheung Vice President

