

Date:

Sep 01, 2020

BAREBONES SYSTEMS, LLC. Applicant:

1215 EAST WILMINGTON AVENUE -STE.

140 SALT LAKE CITY UT 84106

VIAN Attn:

Sample Description:

One (1) style of submitted sample said to be :

Item Name **Enamel Salad Plate Set (Eggshell)**

CKW-392 Item No. Date Sample Received

Aug 20, 2020 Aug 20, 2020 to Aug 28, 2020 Testing Period



Tests conducted:

As requested by the applicant, refer to attached page(s) for details.

To be continued







Conclusion:

Tested Article Tested component of Submitted samples

Standard European Council Directive 84/500/EEC Article 2 and Commission Directive 2005/31/EC and Regulation 1935/2004

on leachable Lead and Cadmium released from ceramic article intended to come into contact with foodstuff

EU Technical Guide Council of Europe Resolution

CM/Res(2013)9 on metals and alloys Used in Food Contact Materials and Articles on specific migration of heavy metal

Comment: The scope of the standard was not applicable to the submitted samples. Testing was conducted with reference to the test method and requirements as stated.

Authorized by:

For Intertek Testing Services Shenzhen Ltd. Guangzhou Branch, Hardlines

Victor T.J/Wang Assistant General Manager



Result

Pass

See comment







Tests Conducted

Leachable Lead and Cadmium Content - Internal Surface 1

As per European Council Directive 84/500/EEC and Commission Directive 2005/31/EC by Atomic Absorption Spectrophotometric (AAS) analysis.

Test condition: 4% acetic acid, 20-24°C, 24 hours

Tested Sample/ component(1):

Tested Specimen	Surface Area (dm²)	Leaching Volume (ml)	Result					
			Le	ad	Cadmium			
			mg/dm ²	mg/l	mg/dm ²	mg/l		
(1)	3.63	420	ND(<0.05)	ND(<0.05)	ND(<0.03)	ND(<0.03)		
(2)	3.63	420	ND(<0.05)	ND(<0.05)	ND(<0.03)	ND(<0.03)		
(3)	3.63	420	ND(<0.05)	ND(<0.05)	ND(<0.03)	ND(<0.03)		
(4)	3.63	420	ND(<0.05)	ND(<0.05)	ND(<0.03)	ND(<0.03)		
		Average :	ND(<0.05)	ND(<0.05)	ND(<0.03)	ND(<0.03)		
	Limit (ca	tegory 1/3):	0.8	1.5	0.07	0.1		

ND = Not detected

Tested Component: (1) White/blue/black enamel (internal surface of plate).



intertek.com.cn

intertek.com





Tests Conducted

2 Release Testing on Metals and Alloys Used in Food Contact Materials and Articles

With reference to EU Technical Guide "Council of Europe Resolution CM/Res(2013)9 on metals and alloys Used in Food Contact Materials and Articles". Migration test was carried out and heavy metal content was determined by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES) and Inductively Coupled Plasma Mass Spectrometer (ICP-MS).

I. Test Condition:

Temperature: 70 °C Time: 2 hours

II. Test Result:

Food simulant: Citric acid (5 g/L)

Tostod component (1):											
Tested component (1):											
	Result 1st	Result 2 nd	Result 1st	Result 3 rd	Reporting	7*Limit	Limit				
Elements	test	test	test+Result	test	Limit	7*Limit	Limit				
	(mg/kg)	(mg/kg)	2 nd test (mg/kg)	(mg/kg)	(mg/kg)	<u>(mg/kg)</u>	(mg/kg)				
Silver (Ag)	ND	ND	ND	ND	0.05	0.56	0.08				
Aluminium (AI)	ND	ND	ND	ND	1	35	5				
Chromium (Cr)	0.04	ND	0.04	ND	0.02	1.75	0.250				
Cobalt (Co)	ND	ND	ND	ND	0.01	0.14	0.02				
Copper (Cu)	ND	ND	ND	ND	0.5	28	4				
Iron (Fe)	ND	ND	ND	ND	1	280	40				
Manganese (Mn)	ND	ND	ND	ND	0.1	12.6	1.8				
Molybdenum(Mo)	ND	ND	ND	ND	0.02	0.84	0.12				
Nickel (Ni)	0.1	ND	0.1	ND	0.1	0.98	0.14				
Tin (Sn)	ND	ND	ND	ND	10	700	100				
Vanadium (V)	ND	ND	ND	ND	0.005	0.07	0.01				
Zinc (Zn)	ND	ND	ND	ND	1	35	5				
Antimony (Sb)	ND	ND	ND	ND	0.01	0.28	0.04				
Arsenic (As)	ND	ND	ND	ND	0.001	0.014	0.002				
Barium (Ba)	ND	ND	ND	ND	0.1	8.4	1.2				
Beryllium (Be)	ND	ND	ND	ND	0.01	0.07	0.01				
Cadmium (Cd)	ND	ND	ND	ND	0.001	0.035	0.005				
Lead (Pb)	ND	ND	ND	ND	0.005	0.070	0.010				
Lithium (Li)	ND	ND	ND	ND	0.010	0.336	0.048				
Mercury (Hg)	ND	ND	ND	ND	0.003	0.021	0.003				
Thallium (TI)	ND	ND	ND	ND	0.0001	0.0007	0.0001				
Magnesium(Mg)	ND	ND	ND	ND	1	-	-				
Titanium(Ti)	ND	ND	ND	ND	1	-	-				

ND = Not detected(less than reporting limit)









Tests Conducted

Remark: The submitted sample is a repeated use article. The migration test was carried out three times on the same article. The sum of the results of the first and second tests should not exceed seven times the limit (Result 1st test + Result 2nd test < 7 * limit) and the Result 3rd test shouldn't exceed the limit.

Ratio of food contact surface area to volume of component (1) used to establish the compliance of material or article = $1.20 \text{ dm}^2 : 200 \text{ mL}$.

Tested component(s): (1) Gold color stainless steel (binding of plate).

End of report

The statements of conformity reported have considered the decision rule agreed, namely that Intertek have taken account of measurement uncertainty as calculated by Intertek, and applied according to ILAC-G8/09:2019 (Non-binary acceptance based on guard band w = U) except designation from the customer, regulation or test specification.

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. This report shall not be reproduced unless with prior written approval from Intertek Testing Services Shenzhen Limited, Guangzhou Branch.



Page 5 of 5