

Test Report

Number: GZHH00376938

Applicant: BAREBONES SYSTEMS,LLC.
1215 EAST WILMINGTON AVENUE -STE.
140 SALT LAKE CITY UT 84106

Date: Sep 01, 2020

Attn: VIAN

Sample Description:

One (1) style of submitted sample said to be :
Item Name : Enamel Salad Plate Set (Eggshell)
Item No. : CKW-392
Date Sample Received : Aug 20, 2020
Testing Period : Aug 20, 2020 to Aug 28, 2020

GZHH00376938



Tests conducted:

As requested by the applicant, refer to attached page(s) for details.

To be continued



Page 1 of 3



Test Report

Number: GZHH00376938

Conclusion:

<u>Tested Article</u>	<u>Standard</u>	<u>Result</u>
Submitted articles	U.S. F.D.A. CPG Sec. 545.400 (CPG 7117.06) and Sec. 545.450 (CPG 7117.07) on ceramic ware	See comments
Tested component(s) of submitted sample	FDA General Recognized As Safe (GRAS)	Pass

Comment:

The testing scope of the standard(s) were not applicable to the submitted samples. However, the test results of the samples met the related requirements as stated in this report.

Authorized by:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch, Hardlines



Victor T.J. Wang
Assistant General Manager



Page 2 of 3

Intertek Testing Services Shenzhen Limited, Guangzhou Branch

深圳天祥质量技术服务有限公司广州分公司

#111 TCL Cultural Industry Park, Guangpu-west Road, Science City, High and New Technology Industrial Development Zone, Guangzhou. / Block E, No.7-2 Caipin Road, Guangzhou Science City, GETDD, Guangzhou.

广州高新技术开发区科学城光谱西路 69 号 TCL 文化产业园汇创空间 111/广州经济技术开发区科学城彩频路 7 号之二 E 栋(510663)

Tel +8620 8213 9688
Fax +8620 3205 3537
intertek.com.cn
intertek.com



Test Report

Number: GZHH00376938

Tests Conducted

1 Leachable Lead and Cadmium Content - Internal Contact Surface

As per U.S. FDA CPG Sec. 545.400 (CPG 7117.06) and Sec. 545.450 (CPG 7117.07) and A.O.A.C. Official Methods of Analysis 18th Edition (2005) Method 973.32 by Atomic Absorption Spectrophotometric analysis.

<u>Tested Article</u>	<u>Volume of Leaching Solution (ml)</u>	<u>Lead (ppm)</u>	<u>Cadmium (ppm)</u>
(1)	420	<0.05	<0.03
(2)	420	<0.05	<0.03
(3)	420	<0.05	<0.03
(4)	420	<0.05	<0.03
(5)	420	<0.05	<0.03
(6)	420	<0.05	<0.03
Average :		<0.05	<0.03
Limit : (U.S. FDA Flatware)		3.0	0.5

ppm = parts per million = mg/l

< = Less than

Tested Component : (1) White/blue/black enamel (internal surface of plate).

2 Total Chromium content

By acid digestion followed by Inductively Coupled Plasma Emission Spectroscopic analysis.

<u>Element</u>	<u>Result (%)</u>	<u>Reporting limit (%)</u>	<u>Limit (%)</u>
	(1)		
Chromium (Cr)	18.24	0.01	16 min

Tested Component : (1) Gold color stainless steel (binding of plate).

End of report

The statements of conformity reported have considered the decision rule agreed, namely that Intertek have taken account of measurement uncertainty as calculated by Intertek, and applied according to ILAC-G8/09:2019 (Non-binary acceptance based on guard band $w = U$) except designation from the customer, regulation or test specification.

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. This report shall not be reproduced unless with prior written approval from Intertek Testing Services Shenzhen Limited, Guangzhou Branch.



Page 3 of 3

Intertek Testing Services Shenzhen Limited, Guangzhou Branch

深圳天祥质量技术服务有限公司广州分公司

#111 TCL Cultural Industry Park, Guangpu-west Road, Science City, High and New Technology Industrial Development Zone, Guangzhou. / Block E, No.7-2 Caipin Road, Guangzhou Science City, GETDD, Guangzhou.

广州高新技术产业开发区科学城光谱西路 69 号 TCL 文化产业园汇创空间 111/广州经济技术开发区科学城彩频路 7 号之二 E 栋(510663)

Tel +8620 8213 9688
Fax +8620 3205 3537
intertek.com.cn
intertek.com

