

## TEST REPORT

REPORT No.: DG8200804-12538E

Date: August 19, 2020

Page 1 of 6

**BAREBONES SYSTEMS,LLC.**  
**1215 East Wilmington Avenue-Ste.140 Salt Lake City, UT 84106**

Report on the submitted samples said to be:

Sample Description : Zippered Lantern Storage Bag  
Style/Item No. : LIV-285  
Brand : BAREBONES  
Country of Origin : CHINA  
Country of Destination : USA  
Sample Receiving Date : August 5, 2020  
Testing Period : From August 5, 2020 to August 19, 2020  
Results : Please refer to next page(s).

Signed for and on behalf of BACL

Checked by :



Chevy Feng

Approved by :



Kithy Li

# TEST REPORT

REPORT No.: DG8200804-12538E

Date: August 19, 2020

Page 2 of 6

\*\*\*\*\*  
**Summary of Test Results:**

**TEST REQUEST**

**CONCLUSION**

A	US California Proposition 65 on Lead content	Pass
B	US California Proposition 65 on Phthalates (DBP, BBP, DEHP, DnHP, DINP and DIDP) content	Pass

Pass= Meet the Requirement of Client

\*\*\*\*\*

# TEST REPORT

REPORT No.: DG8200804-12538E

Date: August 19, 2020

Page 3 of 6

## Results:

### Tested part(s):

- |   |                                       |
|---|---------------------------------------|
| (1) Charcoal coated leather(body patch)     | (5) DK. grey plastic(zipper teeth)    |
| (2) Brown coated leather(handle)            | (6) LT. gunmetal metal(zipper puller) |
| (3) Black PU with PVC(bottom, semi-product) | (7) LT. gunmetal metal(zipper slider) |
| (4) Black elastic(top lining)               | (8) Brown coating(edge of body patch) |

Remark 1: Sample (3) was tested by semi-product according to the applicant's request, The applicant will undertake all differences and risk.

Remark 2: The test result of sample (3) is shown retest result, and the retest sample was provided by client on August 17, 2020.

## A. US California Proposition 65. on Lead content

### Total Lead Content (In surface-coating)

Test method: With reference to CPSC-CH-E1003-09.1, by acid digestion and analysis was performed by Atomic Absorption Spectrometry (AAS).

Item	Unit	MDL	Results	Client's Limit
			(8)	
Lead Content (Pb)	mg/kg	10	N.D.	90
<b>Conclusion</b>	<b>/</b>	<b>/</b>	<b>Pass</b>	<b>/</b>

### Total Lead Content (In substrate)

Test method: With reference to CPSC-CH-E1001-08.3/ CPSC-CH-E1002-08.3, by acid digestion and analysis was performed by Atomic Absorption Spectrometry (AAS).

Item	Unit	MDL	Results				Client's Limit
			(1)+(2)	(3)	(4)+(5)	(6)+(7)	
Lead (Pb)	mg/kg	10	N.D.	13	N.D.	26	100
<b>Conclusion</b>	<b>/</b>	<b>/</b>	<b>Pass</b>	<b>Pass</b>	<b>Pass</b>	<b>Pass</b>	<b>/</b>

# TEST REPORT

REPORT No.: DG8200804-12538E

Date: August 19, 2020

Page 4 of 6

Note:

- N.D. = Not Detected or less than MDL
- MDL = Method Detection Limit
- mg/kg=ppm
- "+"= Mixed, The admixture of specimen is tested as a whole(part) which according to the applicant's request, the result of report as average value because of the whole specimen is regarded as constituting from the homogeneous material. If the testing of specimen may have the obvious difference, and the result may exceed the number in this report. The applicant will undertake all differences and risk.
- Photo is included.

## **B. US California Proposition 65. on Phthalates (DBP, BBP, DEHP, DnHP, DINP and DIDP) content**

Test method: With reference to CPSC-CH-C1001-09.4, by solvent extraction and Analysis was performed by gas chromatographic-mass spectrometer (GC-MS)

Item	Unit	MDL	Results				Client's Limit
			(1)+(2)	(3)	(4)+(5)	(8)	
Dibutyl Phthalate (DBP)	mg/kg	30	N.D.	106	N.D.	N.D.	1000
Benzylbutyl Phthalate (BBP)	mg/kg	30	N.D.	N.D.	N.D.	N.D.	1000
Bis-(2-ethylhexyl) Phthalate (DEHP)	mg/kg	30	N.D.	70	N.D.	37	1000
Di-n-hexyl Phthalate (DnHP)	mg/kg	30	N.D.	N.D.	N.D.	N.D.	1000
Diisononyl Phthalate (DINP)	mg/kg	100	N.D.	N.D.	N.D.	N.D.	1000
Diisodecyl Phthalate (DIDP)	mg/kg	100	N.D.	N.D.	N.D.	N.D.	1000
<b>Conclusion</b>	<b>/</b>	<b>/</b>	<b>Pass</b>	<b>Pass</b>	<b>Pass</b>	<b>Pass</b>	<b>/</b>

Note:

- N.D. = Not Detected or less than MDL
- MDL = Method Detection Limit
- % = Percentage by weight
- 0.1% = 1000mg/kg, mg/kg = ppm
- "+"= Mixed, The admixture of specimen is tested as a whole(part) which according to the applicant's request, the result of report as average value because of the whole specimen is regarded as constituting from the homogeneous material. If the testing of specimen may have the obvious difference, and the result may exceed the number in this report. The applicant will undertake all differences and risk.
- Photo is included.

\*\*\*\*\*

## TEST REPORT

REPORT No.: DG8200804-12538E

Date: August 19, 2020

Page 5 of 6

Photograph of Sample



BACL authenticate the photo on original report only

# TEST REPORT

REPORT No.: DG8200804-12538E

Date: August 19, 2020

Page 6 of 6

## Directions:

1. This report cannot be reproduced except in full, without prior written approval of the Company.
2. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
3. This report is valid only with a valid digital signature. The digital signature may be available only under the Adobe software above version 7.0.
4. Otherwise required by the applicant or Product Regulations, Decision Rule in this report did not consider the uncertainty.
5. The information which provided by the applicant, such as sample description, sample name ,material component, style/item No. , P.O. No. , manufacture, age phase, the laboratory is not responsible for its authenticity and this information can affect the validity of the result in the test report.
6. The test samples were in good condition before testing.
7. The extended uncertainty given in this report is obtained by combining the standard uncertainty times the coverage factor K with the 95% confidence interval.

\*\*\* End of Report \*\*\*